5.02 Timber Processing

- a. tools
- b. felling
- c. pit sawing
- d. sawmills
- e. woodworking machinery
- f. seasoning
- g. preservative treatments
- h. antproofing

a. tools

English axes seem to have been singularly inadequate, not only in Australia but in Upper Canada, where Governor Simcoe commented:

Particular attention must be given to the tempering of the Steel. without which the Axe will be of no value as is the case of those already sent over. The little attention given to this particular in England has already deprived her of a great part of the manufactory of edge tools.

He accompanied this with a sample American axehead, saying that if it could not be duplicated England could forget about selling axeheads in Upper Canada. A little later he wrote even more forthrightly to Evan Nepean that 'The axes sent to this Country are so carelessly fabricated as to be totally incompetent to any Service whatever.'2

Australian hardwoods were generally tougher than Canadian timbers, and even more unfamiliar to British settlers, and there were problems even in cutting down any of the more durable trees suitable for building. Governor Phillip complained from the first that 'bad tools are no kind of use,'³ and four years later was still asking for saws and axes, as those from England had worn out. Some attempts were being made to forge tools locally from scrap iron, but with very little success.⁴ There must have been some recognition of the problem in England at least by 1851, when at the Great Exhibition R Thomas of Birmingham showed 'American wedge axes' of his own manufacture and Spear & Jackson of Sheffield showed an 'American wedge axe, with solid steel edge', presumably of their own manufacture.⁵

Morton Herman, The Early Australian Architects and their Work (Sydney 1954), p 4, citing Historical Records of News South Wales, I, part II, p 556.

Herman, Early Australian Architects, p 4, citing Historical Records of News South Wales, I, part II, p 643.

London, Great Exhibition of the Works of Industry of all Nations, 1851, Official Descriptive and Illustrated Catalogue (3 vols, London 1851), II, p 606, though Spear &

J I Rempel, Building with Wood and other aspects of Nineteenth-Century Building in Central Canada (Toronto 1980 [1967]), p 362.

Rempel, Building with Wood, p 365.

By the 1820s distinctive local tools had begun to develop, and Peter Cunningham stated that' edge tools require to be particularly well tempered to withstand our hard woods.¹⁶ as he said:

The common English sale [probably meaning 'shell'⁷] gimlets are either soon broken at the point by our woods, or else the handle becomes loose. The best method is to file off a portion of the screw, sharpening the remains to a point, give the gimlet a half turn backwards every bore you make, and clean it frequently. Centre-bits are by far the most expeditious, however, and a dozen sets each of bits for boring nail-holes of all sizes ought to be taken out.⁸

The inadequacy of the tools available, and the initial lack of understanding of the local species, delayed the adoption even of practices which were common in Britain. Even weatherboard cladding, widespread in Wales, Kent and Sussex, made only a belated appearance, as will appear below. Nonetheless, most tools were of standard overseas types, mainly British at first but increasingly American as time wore on. But there were also some saws imported from Germany. 10

The mortice axe seems to have been an exception. It was used in Australia for both mortices and grooves. A mortice was created by first drilling two holes with an auger, then chopping out the intervening timber. A groove, such as that required in the top or bottom plate of a vertical slab structure, or the post of a horizontal slab or a wattle and daub structure, was similarly formed by drilling a whole series of holes first, then chopping out the balance. The puzzling aspect is that the tool was not known in England, though there is some evidence to suggest that it may have been used in the eighteenth century.¹¹

Cross-cut saws underwent a similar process to that for axes. In the 1850s John Capper recommended to the settler a 'crosscut saw, six feet plate at least; seven feet better, square teeth; files for ditto, at least half-a-dozen; and saw-set. In 1851 Spear & Jackson of Sheffield showed a crosscut and other saws, as well as a range of other tools, and they showed an equally large range three decades later at the Melbourne International Exhibition of

Jackson's may not have been in regular production, as it was described as a 'specimen of ...'.

Peter Cunningham, Two Years in New South Wales (2 vols, London 1827), II, p 165.

H A Salaman, *Dictionary of Woodworking Tools* (Mendham [New Jersey] 1997 [1989 (1975)]), p 278.

Peter Cunningham, Two Years in New South Wales (2 vols, London 1827), II, p 166.

Trudy West, *The Timber-Frame House in England* (Newton Abbot [Devonshire] no date), p 88.

Argus, 10 April 1852, p 1, where Symons & Perry advertise the auction of German handsaws and iron back saws..

Thompson & Turner, 'The Mortice Axe', p 12...

¹² Capper, *Philips' Emigrant's Guide*, p 45.

London, Great Exhibition, 1851, *Catalogue*, II, p 606. Ibbotson Brothers & Co of Sheffield, also showed a very wide range of saws, and Samuel Biggins & Sons, also of Sheffield, a more limited range: ibid, II, pp 614, 617.

1880, where they were awarded a gold medal, ¹⁴ while later in the decade they were reported to have taken 'a great hold on the market' for saws, ¹⁵ though this was by no means a monopoly. In 1886 F Lowe & Co of Melbourne were advertising as agents for the saws and other products of W Tyaack, Sons & Turner, of Sheffield. ¹⁶

Americans were more innovative, and by the 1870s Henry Disston & Sons of Philadelphia were reported to have improved the shape of saw handles, the manner of fixing the blade to the handle, and the shape of the handsaw blade, making it lighter and more convenient. Then at Melbourne in 1888-9 Disstons exhibited their circular and flat saws, and their 'saw grinding machinery', and they were soon to take a substantial share of the local market. Up to this point crosscut saws would mostly have been of the type called 'peg tooth' to distinguish them from the more elaborate forms. The teeth were triangular, and sometimes spaced quite widely, with a small straight recess in the space between. During the 1880s saws with 'square teeth' were introduced in the United States, typically with an arrangement of two clearing teeth alternating with one cutting tooth.

In 1897 a Tasmanian, A Goold, introduced saws with teeth in the shape of a large inverted 'M' instead of a single peg tooth, but did not patent the design.²⁰ This is not surprising, as it appears to have been an American invention, and in 1876 was shown at Philadelphia by Eben Moody of Boynton, New York. ²¹ Salaman, however, describes the M-tooth type as a popular one dating from the fifteenth century and implies that the Tasmanian type is different, though he does not illustrate it. 22 Disstons, and a British company, apparently Spear & Jackson, immediately began to produce this type, which became known as the Tasmanian pattern. This was soon recognised as the best, and other British makers began to produce it.²³ About the turn of the century Disston saws won all competitions, followed by Simmonds, then Spear & Jackson. At the International Wood Chop and Sawing Competition of 1899, however, neither Spear & Jackson nor any other British firm entered, so the competition was between the Americans Simmonds, H Disston & Co, and the eventual winners, the Atkins saw Co.²⁴ Henceforward the 'Tasmanian tooth' as well as the plain or peg tooth saw was a feature of

Melbourne International Exhibition, 1880-1881, Official Record (Melbourne 1882), p 614.

Australasian Builder & Contractor's News, 3 September 1887, p 268.

Australasian Ironmonger, 1 December 1886, advertisement p vi.

¹⁷ McHardy, p 132.

Centennial International Exhibition 1888-1889, *Official Record* (Melbourne 1890), pp 833, 837.

C D Elliott, *Technics and Architecture* (Cambridge [Massachusetts] 1992), p 15.

Val Quanchi, 'World Competition to Ascertain the Best Saw and Axe', *Tool Chest,* XI, 1 (February 1999), p 27.

McHardy, p 132. [this seems to be his report on the Philadelphia exhibition - get details]

Salaman, *Woodworking Tools*, p 416.

Quanchi, 'The Best Saw and Axe', p 27.
Quanchi, 'The Best Saw and Axe, pp 28-9.

the Australian market, and though Disstons had not won the competition, they appear to have become the leading suppliers.²⁵

In about 1902 Robert Kaleski illustrated the 'Lightning' saw, which was available in Australia and had a W rather than an M tooth - that is, each upstand had three points rather than two. The M tooth variety, which Disstons called 'the Lumberman', was seen as an intermediate type, ²⁶ and was probably much the same as Goold's Tasmanian pattern, though Disstons themselves seem to have adopted the name 'Tasmanian' at a later date. In 1924 Colton, Palmer and Preston of Adelaide stocked both Tasmanian tooth and 'Great American Tooth' Disston crosscut saws. ²⁷ From at least 1930 onwards D & W Chandler of Melbourne sold 'Tasmanian Tooth (Disston) Ground' and 'Disston Patent Ground' saws. ²⁸ It is interesting, by comparison, to find that a leading French supplier in around 1900 advertised nothing but uniformly toothed saws. ²⁹

Some other tools evolved significantly during the period of Australian settlement, though the changes were not initiated here. One was the woodworker's plane, a tool known since Roman times and recognisably the same in all salient respects. In 1829 a United States patent was issued for a plane with a metal sole, and in 1843 W Foster received a patent for an improvement whereby the thickness of the shaving was varied by turning a screw. In 1854 a screwed clamp was introduced instead of a wedge, to secure the iron. In 1858 Leonard Bailey received a patent for a friction device to adjust the cutter, which was not very effective. However he introduced a number of further improvements until 1869, when he sold his business to the Stanley Rule and Level Co, and himself became head of their plane department. The Stanley all-metal plane followed in due course. A full range of Stanley planes was offered by Colton, Palmer & Preston in the 1920s. Preston in the 1920s.

b. felling

One of the best descriptions of felling a tree is that of a settler of the 1850s, quoted in W T Pyke's *Bush Tales:*

Danks, *Wood-Workers' Catalogue*, p 9. A 'Jarrah' or 'M tooth' crosscut saw, in which the tooth shape is similar but perhaps slightly simplified, was later being made by Simmonds and by Sanderson Bros. & Newbould: McPherson's, *Catalogue*, p 25.

Robert Kaleski, *The Australian Settler's Guide* (Anthony Hordern & Sons, Sydney, no date [c 1902]), pp 7, 8, 11.

Colton, Palmer & Preston, Ltd., Tools for all Trades (Adelaide [1924), p 47.

D. & W. Chandler Ltd, *General Hardware Catalogue Issue No 43* (Melbourne no date [?c1930], p 6, and subsequent catalogues.

Comptoire de l'Industrie, L Laurent, Carrée & Binoche [successors of L Laurent & Carrée], *Tarif pour Sciences Mécaniques (No. 10)* (nd), bound with Comptoire de l'Industrie, L Laurent & Carrée, *Tarif des Fournitures Générales pour l'Industrie* (Reims [c 1890]).

Stanley Works (G.B.) Ltd, *A Brief History of the Woodworker's Plane* (Sheffield, no date), passim.

Colton, Palmer & Preston, Tools for all Trades, pp 40-41

First, it is requisite to seek a tall, straight, stringy bark tree of good size, and after cutting a small piece out to see how the grain runs, the next thing is to 'ring it,' as it is technically called; that is, to cut off a strip of bark all round the tree for about a foot in width, and applying a saw to the side on which the tree leans, cut it until the saw is jammed. At this point an axe is used to cut underneath the butt, in order to have the end of the trunk square; after this the other side must be cut, and the tree will presently fall. Sometimes when the tree happens to stand very straight, it will need a wedge to be inserted in the cut made by the saw, and driven in until the tree falls. ³²

The aim in cutting a tree was to get above the 'buttresses' or flared ribs at the base, leading to the roots, for the straight part of the trunk was much less in diameter and proportionately easier to cut. But this required the construction of a platform for the men to stand on, or the insertion of logs or planks into the trunk as cantilevers for the same purpose. A device intended to reduce the strain of supporting the saw involved hanging it from struts fixed into the trunk above, so that it could be rocked back and forth freely, but nothing seems to have come of this.³³

English axes had the same limitations as other English tools. Diemen's Land in 1817 William Thornley tried to cut down a tree using heavy broad axes which he had brought from England, but had much more success with the 'camp axes' which he bought in Hobart, and which were 'much longer in the handle and narrower in the blade', though it is not clear where they were made.³⁴ In Western Australia from 1829 the settlers also found English axes unsuitable for local hardwoods, and got around the problem mainly by ringbarking and burning to clear the land. 55 Even in 1841 James Allen of Brownhill Creek, South Australia, wrote 'Few axes that are sent here will stand against our wood, without being re-hardened'. By the 1820s distinctive local tools had begun to develop, at least in the east, and Peter Cunningham stated 'Our felling axes are long and narrow, to penetrate our iron woods more readily, and with one somewhat larger and narrower still, the mortices are cut in the posts. 37 This implies that axes different from the English standard were used, but it may be that this was a question of selecting one of the less usual English types rather than redesigning the implement entirely.

Robert Irving has explained that the English felling axe, though unsuitable for the job, remained the norm in Australia until the American axe was imported,

W T Pyke, *Bush Tales by old Travellers and Pioneers* (Melbourne 1893 [1888]), p 71.

John Vader, *Red Cedar, the Tree of Australia's History* (French's Forest [New South Wales] 1988]), p 85.

William Thornley [ed J S Mills], *The Adventures of an Emigrant in Van Diemen's Land* (Adelaide 1973 [1840s]), pp 40-41.

J M R Cameron, 'Patterns on the Land, 1829-1850', in J Gentilli [ed] Western Landscapes (Nedlands [Western Australia] 1979), p 209.

Colin Kerr, 'An Exelent Coliney' (Adelaide 1978), p 130.

Peter Cunningham, Two Years in New South Wales (2 vols, London 1827), II, p 165.

probably in the 1860s.³⁸ It may have been somewhat earlier than this, for the problem had been obvious from the beginning. In Canada it was said in 1838 that 'an axe has not yet been manufactured in England in the form or temper which long experience has proved best. A good chopper will do treble the work with an American made axe than he could do with an English made one.³⁹ In New Zealand George Earp wrote in 1853 that carpenters:

should always have a good assortment of tools ...

.. make a selection of American axes, all others are of no use ... the timber of New Zealand will try the goodness of the best article.⁴⁰

In fact suitable axes began to be made in Australia at about this time, and John Capper recommended the settler to equip himself with 'a common Australian axe forged in the colony'. Certainly by 1866 axes on the American pattern were being made in Melbourne by Peter Valot, and the judges at the Intercolonial Exhibition considered them virtually indistinguishable from the real thing, made of the finest steel and properly tempered. 42

A German observer commented that the American axe would fell and smooth logs in the same number of hours as the German axe would require days, and it was equally superior to the English type. How the American axe evolved is a mystery, though it has been referred to as a steel version of the Red Indian axe. By 1776 a design had become established in which the head was almost rectangular in side elevation, and indeed the poll or rear of the head actually outweighed the bit, or blade. In addition to this small, heavy head with fat cheeks and a curved cutting edge, it had a long tough hickory handle which could absorb shock. It was swung wide and thrown into the wood, whereas the English axe was used like a chopper, and had a straight short handle carrying a large but light head, with a straight cutting edge and straight tapered cheeks.

David McHardy, reporting on the exchibits at Philadelphia in 1876, usefully illustrated the English and American axe heads. The English type was a blade of fairly uniform thickness, widening at the end to form the eye into which the

Robert Irving, 'The First Australian Architecture' [MArch, University of New South Wales 1975], p 187, citing inter alia Mary Gilmore, *More Recollections* [], pp 145, 146, with a comparative illustration of axe heads from Ralph Hodgkinson, *Tools of the Woodworker* [technical leaflet No 28 of the American Association for State and Local History].

Rempel, *Building with Wood,* p 365.

G B Earp, New Zealand Emigration and the Gold Fields (London 1853), quoted in C P Murphy, 'The Fencible Cottage: Soldier Housing' (MArch, University of Auckland, 1995), p 73.

John Capper [ed D J Golding], *Philips' Emigrant's Guide to Australia* (Melbourne 1973 [London 1855]), p 45.

Intercolonial Exhibition of Australasia, 1866-67, *Official Record* (Melbourne 1867), pp 31, 332.

John Fitchen, *Building Construction before Mechanisation* (Cambridge [Massachusetts] 1986), pp 136-7.

J K Andrews, 'History of Merrigum' (manuscript, Merrigum [Victoria] 1954, copy supplied by Anne Tyson 1997), p 27.

H C Mercer, *Ancient Carpenters' Tools* (Mineola [New York] 2000 [1929]), pp 4, 7.

Andrews, 'History of Merrigum', p 27.

handle was inserted. The American was quite different: the blade widened uniformly back to the eye, and the mass of the head was much greater, This was what was meant by 'fat cheeks'. This axe was easier to work with, more readily removed after the blow, firmer, and not liable to twist in the working. The demand for these was enormous, and many exhibitors produced almost identical models. Prominent amongst these were Collins & Co of NewYork, the Douglas Axe Company of Boston, and Yerkes & PLumb of Philadelphia. 47

Salaman also explains that the English axe had a smoothly curved handle, oval in cross-section, and thickened slightly at the foot. American felling axes had a double curved 'fawn-foot' pattern handle, apparently devised in the midnineteenth century, which permits a fixed grip near the foot with one hand, and a sliding grip with the other. Salaman also illustrates an axe head made in Britain for the Australian market, a heavy version of what is known as the 'Kent' type. This embraces a number of variations, but all with a symmetrical round-shouldered blade, a flat poll (the side opposite the cutting face), and pointed lugs above and below the eye through which the handle is fitted. As

Late in the century settlers in the Goulburn Valley used an American axe called 'The Sharp', made by the Douglas Axe Co, and this gave rise to an idiomatic expression 'swinging Douglas'. 50 By the 1890s the Douglas and other American brands such as Plumb, Underhill, Hubbard, Chopper's Pride Mam, and Lippincoat, had largely displaced English axes such as Elwell and Gipin. In axemen's competitions Plumb and Underhill proved the best, and by 1892 most competitors favoured the Underhill bronze coloured axe. Local blacksmiths were themselves making improved axes, and the United Axemen's Association invited axe competitors and manufacturers to submit ideas for the best axe design. Agreement was reached that the ideal was a blade $5^{1}/4$ to $5^{1}/2$ inches [134-141 mm] wide, a total depth of $7^{1}/2$ inches [192 mm], a half inch [13 mm] pole, a width at the handle of 4¹/₂ inches [115 mm], and a total weight of six pounds [2.72 kg]. Four American companies, but no British ones, were able to supply this.⁵¹ By 1897 90% of competitors preferred American axes despite a general belief that the British ones were of higher quality manufacture. 52 It does not appear, however, that Australia took to the double-sided axe which West Coast lumbermen had adopted in the 1870s. There the motivation was that one side could be used for undercutting, while the other was reserved for hard knots and other work that would quickly dull the edge.⁵³ Such contrasts were perhaps less pronounced in Australian timbers.

47 McHardy, p129.

Salaman, *Woodworking Tools*, p 48; also p 194 for illustrations of fawn-foot handles.

Salaman, *Woodworking Tools*, pp 52 58.

J K Andrews, 'History of Merrigum' (manuscript, Merrigum [Victoria] 1954, copy supplied by Anne Tyson 1997), p 27.

Quanchi, 'The Best Saw and Axe, p 25.

Quanchi, 'The Best Saw and Axe', p 27.

Elliott, Technics and Architecture, p 14.

J C Penny, writing after the turn of the century, refers to the astonishing workmanship of Tasmanian axemen, who produced surfaces as clean and true as if cut by machinery, and who were expert with the broad axe as well as 'the ordinary American axe'. ⁵⁴ In 1898 the English company Brades had taken an interest in the market, and sent out specimen axes, which were judged to be the best yet seen. Brades then sent out a case of axes for the International Wood Chop and Sawing Competition in Tasmania in 1899 and won the competition, notwithstanding the fact that the American Axe and Tool Company had produced their Hollow Concave Axe in January 1899. This latter company had by 1902 acquired many of the other American manufacturers. ⁵⁵ It was this competitive process which established the form of the 'Tasmanian Axe' as manufactured for many years afterwards.

Soon John Danks of Melbourne advertised Plumb's, Collins and Brades (Cockatoo brand) axes in the Tasmanian pattern, each in seven weights from 4 to 51/2 pounds [1.8 - 2.5 kg]. Robert Kaleski favoured either Plumb's, or Kelly's 'Prerfect', which was made by W C Kelly of Indiana and sold by Anthoy Hordern & Co of Sydney (who sponsored his publication). In 1924 Colton, Palmer & Preston stocked the Plumb Tasmanian pattern and the Kelly Standard Hand Made Axe in the Tasmanian pattern, as well as 'Kelly's Perfect Yankee Pattern'. In about 1930 D & W Chandler stocked a range of Plumb's axes, as well as Kelly's 'Perfect' and 'Standard (Tasmanian Pattern)' models. In 1949 McPhersons of Melbourne were similarly advertising Plumb's Tasmanian Pattern, Kelly Dandenong Tasmanian Pattern and Brade's Cockatoo axes.

c. pit sawing

Bulk timber was sawn over a pit, in a manner which was traditional not only in Britain, but in many other parts of the world, ⁶¹ and requires no particular description here. ⁶² According to Robert Irving, some of the first sawpits were dug by the marines and were worked by convicts, who were able to saw some slabs in their own time and barter them for other goods. ⁶³ By April 1788 there were already several such pits on the east side of Sydney Cove and at the

J C Penny, Tasmanian Forestry (Hobart 1910), p 42.

Quanchi, 'The Best Saw and Axe', pp 27-8.

John Danks & Son Pty. Ltd., *Wood-Workers' and Builders' Tool Catalogue* (Melbourne, no date [c 1900]), p 55.

Robert Kaleski, *The Australian Settler's Guide* (Anthony Hordern & Sons, Sydney, no date [c 1902]), p 11.

Colton, Palmer & Preston, *Tools for all Trades*, p 2.

⁵⁹ Chandler, *General Hardware Catalogue 43*, p 3.

McPherson's Limited, *Catalogue* (Melbourne 1949), p 278.

Fitchen, *Building Construction before Mechanisation*, p 274, n 10, refers to pit sawing in the Philippines, Japan, Manchuria, Afghanistan, Turkey and Armenia.

For a brief description see Philip Cox & J M Freeland, Rude Timber Buildings in Australia (London 1969), pp 16-17.

Irving 'The First Australian Architecture', p 154.

head of the Tank Stream.⁶⁴ A sawpit was established in Brisbane by 1826, and measured 15 by 7.2 metres, to accommodate at least four sawyers. It was built with strong posts, wall plates, tie beams and a thatched roof for shade.⁶⁵ Most pits were much smaller, and indeed were built as required close to a stand if timber, or even an individual tree, as an easier option than dragging logs to a more established pit. For example at Arthur's Seat, Port Phillip, in 1845, J McClure dug a pit next to his hut, for reasons of convenience, rather than use an established one further away on the hillside.⁶⁶

There was considerable skill involved in breaking up the log in the most advantageous way, so as to extract the largest amount of good boarding or scantling. In 1803 the Sydney magistrates heard a case in which Andrew Cunningham, a sawyer, had cut the principal part of a log of cedar into boards, 'but in so negligent a manner as to render the boards unfit for use' and had then abandoned the log with the work incomplete. Good sawyers would be engaged by entrepreneurs for substantial periods, and Simeon Lord offered at least six months of guaranteed employment for two or three sawyers to cut cedar, stringybark and 'oaks'. Australian illustrations generally show the open pit saw rather than the framed saw which was the more traditional type.

In the bush travelling sawyers would not dig a full pit, but rely upon a partial excavation with a framework to raise the log over it. This is well described by Alexander Harris, who was cedar cutting in the 1820s:⁷⁰

the ground was so rough and thickly wooded that we had to build a fresh pit to almost every tree. These pits were merely scaffold side-strikes lodged on posts against trees, with long easy skids leading up to them for pitting the log. Sometimes six inches or even a foot of earth might be excavated; but to have dug regular ground pits would have been much too tedious a job; besides which in many places it was so rocky that it would have been impossible. Usually the pits were made very solid; but at other times I felt, I must acknowledge, not quite easy while working under a log of two or three tons weight lodged on side-strikes so small and limber that they sprang up and down two or three inches at every stroke of the saw. ... It was seldom we cross-cut the

[[]Francis Fowkes, attrib], 'Sketch and Description of the settlement at Sydney Cove, &c', 16 April 1788, reproduced in Tim McCormick et al, *First Views of Australia 1788-1825* (Chippendale [New South Wales] 1987), p 37.

L V Dulhunty, Superintendent of Convicts, 'Quarterly Return of Public Labour and Expenditure of Materials at Morton [sic] Bay from the 25th of December 1825 to the 24th March 1826, Inclusive" Archives Office of New South Wales, ref 4/1917, quoted in J G Steel, *Brisbane Town in Convict Days 1824-1842* (St Lucia [Queensland] 1975), pp 52, 54.

W G McCrae to A & G McCrae, 25 February 1845, in G G McCrae [ed], *Letters to Georgiana from her Four Sons* (Arthur's Seat [Victoria] 1962), no page.

Sydney Gazette, 17 July 1803, p 2.
 Sydney Gazette, 2 October 1803, p 4.

See Mercer, Ancient Carpenters' Tools, pp 21-8.

[[]Alexander Harris], Settlers and Convicts (Melbourne 1953 [London 1847]), p 44.

logs off longer than ten or twelve feet, but our planks were sometimes a couple of feet square on the end, or three and four feet in depth, by six, eight, or ten inches in thickness. These planks were always taken out on either one side or other of the heart, that part of the log being too porous and spongy for use. As the various planks came off the pit, they were rolled over into one large stack in some convenient spot a few feet off; and when the whole tree was cut up, this heap was covered over with cabbage tree leaves, on the outside, to protect the timber from the weather.

In 1881 the *Town and Country Journal* published a description of a sawpit which is more detailed, but shows that practice was essentially unchanged after sixty years. The working surface of the pit was formed of the two 'side skids', of 230 mm diameter timber dressed flat on the upper face, and 6 to 7.5 metres long. This carried the 'transoms' or cross pieces, about 1.8 m long and 150 mm square, upon which the log was to be placed, including the 'weighing transom' on which a lever was used to manipulate the log, the 'heading in transom' and the 'heading out transom' at either end, and two others upon which planks were placed to form as stage for the top man to stand on when tailing out. The substructure which supported all this above the ground was basically a small stack of cross logs at one end, and a log leaning onto a convenient tree at the other. The pit was dug beneath to a sufficient depth to allow about 150 mm clearance between the pitman's head and the transoms. Two rolling up skids, 3.5 to 5 metres long, leaned against the side of the structure, and the log was manoeuvred up these into its position.⁷¹

However traditional practices were not unchallenged, for some time previous to this the same journal had relayed a report from the *Scientific American* of what was not actually a pit saw but an 'improved cross cut sawing machine'. It was a device which allowed the operator to sit on an inclined bench and use his muscles more effectively than in the ordinary sawing process. There is no evidence that the machine reached Australia.⁷²

d. sawmills

The timber sawmill has been surmised to date from as early as the fourth century AD, ⁷³ and sawmills operated both by water wheels and windmills are said to have been used in medieval Germany. Villard de Honnecourt's sketchbook, of the thirteenth century, shows a reciprocating saw driven by water, ⁷⁴ and there are a number of apparent references to sawmills in the

Town and Country Journal, 24 December 1870, p 12.

Town and Country Journal, 4 June 1881, p 1077.

George Gregory, A New and Complete Dictionary of Arts and Sciences (3 vols Philadelphia 1816), sv Saw-Mills, quoted in O W Carroll, 'Mr. Smart's Circular Saw Mill c. 1815', in APT Bulletin, V, 1 (1973), pp 58-64.

Akira Satoh [ed Ralph Morton], *Building in Britain, the Origins of a Modern Industry* (Aldershot [Hampshire] 1995 [1986]), p 133. Mercer, *Ancient Carpenters' Tools,* p 6, refers to John Beckman, *A History of Inventions and Discoveries and Origins* (London

early fifteenth century, all of which can be assumed to have used an up-and-down motion. Peterson reports that mechanical sawmilling appeared in the United States in 1611, technicians having been recruited in Hamburg 'to build Saw Mills & Sea them at ye falls. The Dutch were also pioneer sawmillers, and by 1633, when the first sawmill was opened in Massachusetts they were already operating sawmills in New York. In 1646 Joseph Jenks of Massachusetts received a patent for improved sawmills and scythes, which was in fact the first patent issued in the United States for a mechanical invention.

In 1663, when much sawn timber was still imported into Britain from Holland, the first water-powered sawmill in England is said to have been built, but torn down again by Luddites,⁷⁹ whereas by this time hundreds of mills were in operation by the British settlers of New England.⁸⁰ In the 1760s the Society of Arts awarded a premium to James Stansfield for the design of a water-powered sawmill, which was actually constructed in Limehouse by one Dingley, a timber merchant. Though it was - similarly - burnt down by a mob of sawyers, it was then rebuilt, and sawmills were henceforth a permanent feature of the British timber industry, the water-powered type being at first known as the 'Norway engine', doubtless reflecting its origin.⁸¹

The circular saw is claimed to have been invented in England by John Mainwaring in the 1770s and sold to George Smart in 1799, 82 though it has also been said that it was invented by Samuel Miller of Southampton in 1772, 83 or that circular saws - having been long used in Holland - were

^{1872-7),} as having half a dozen interesting pictures, including gang saws (with more than one blade).

Gregory, v Saw-Mills, loc cit.

C E Peterson, 'Early Lumbering: a Pictorial Essay', in Brooke Hindle [ed], America's Wooden Age: Aspects of its Early Technology (Tarrytown [New York] 1975); Illustrated Register of the Centennial Exhibition, Philadelphia, 1876, and of the Exposition Universelle, Paris, 1878 (New York 1879), p 39. Mercer, Ancient Carpenters' Tools p 27, quotes J L Bishop, History of American Manufacturers (Philadelphia 1864) as showing the mechanical sawmill to have been used at the Newichewannock Falls, New Hampshire, before 1635.

F H Norton, Illustrated Register of the Centennial Exhibition, Philadelphia, 1876, and of the Exposition Universelle, Paris, 1878 (New York 1879), p 66.

Nathan Rosenberg, 'America's Rise to Woodworking Leadership', in Hindle, *America's Wooden Age*, p 42.

Norton, Centennial Exhibition, p 39.

Hugh Morrison, Early American Architecture from the First Colonial Settlements to the National Period (New York 1952), p 33, quoting James E Defebaugh, History of the Lumber Industry of America (Chicago 1907), II, p 9.

Taylor, 'Softwood Framing', p 24, ref John Reynolds, *Windmills and Watermills* (Praeger, New York 1970).

Wyatt Papworth [ed], *The Dictionary of Architecture* (London 1852-92), sv Saw; see also Hentie Louw, 'The Mechanisation of Architectural Woodwork in Britain', *Construction History*, VIII (1992), p 22. Carroll gives Smart's name as George, and cites the description and illustration in Gregory. Elliott, *Technics and Architecture*, p 9, refers to a British patent of 1777 for a circular saw - presumably that of Mainwaring.

Rosenberg, 'America's Rise', p 46. Satoh, *Building in Britain*, p 133, attributes the invention of the circular saw to Walter Taylor and his father, of Southampton, in 1790: ref *Builder*, VIII (1850), pp 136-7; *MPICE*, XVII (1857-8), p 18.

introduced to England by General [Samuel] Bentham. ⁸⁴ Certainly in 1806 Marc Brunel patented improved circular sawing machinery, on the clear basis that the fundamental machine was already known. ⁸⁵ Circular sawmills were used at the Portsmouth Dockyard and elsewhere, but even in the 1820s were not widely adopted in England. ⁸⁶ Circular sawmills are claimed to have reached the United States in 1814, ⁸⁷ and machine sawn timber dating from about 1815 has been found there, ⁸⁸ though not proved to be locally produced. However it took half a century for the mechanical sawmill to reach Australia. In the mid-nineteenth century circular saws were made of plates of polished sheet steel, toothed regularly by using a dividing engine by means of

The first mechanical sawmill in Australia was a water-powered one established near Hobart in 1825. Peter Degraves and Major Hugh McIntosh acquired land on the face of Mount Wellington in 1824 or 1825, and here Degraves put up a sawmill which he had brought with him from Britain, supplied by one Barton, a steam engine maker and millwright of Falcon Square, London. Degraves and McIntosh employed an overseer and twenty timber getters and mill hands. Despite insolvency proceedings from 1826 to 1831 Degraves persisted, and later built a second mill. ⁸⁹ J C Penny, who credits Degraves with building the first Tasmanian sawmill at the Cascade in the 1840s, is perhaps referring to this second mill, and it was closely followed, according to Penny, by Richard Hill's mill at Hospital Bay. ⁹⁰ By 1829 Alexander Berry had a sawmill (which must have been water-powered) operating at Shoalhaven. ⁹¹

Water powered flour mills were not uncommon, especially amongst the private settlers, ⁹² all of them potentially capable of being used for sawmilling

W Harris et al, *The Oxford Encyclopaedia* (7 vols, Oxford 1828), sv Saw-Mills.

Repertory of Arts, 2nd series, viii, 47 (April 1896), pp 343-6 & pl xiv.

⁸⁶ Harris, Oxford Encyclopaedia, sv Saw-Mills.

Rosenberg, 'America's Rise', p 46, citing R C Loehr, 'Saving the Kerf: the Introduction of the Band Saw Mill', *Agricultural History*, July 1949, pp 168-9.

Carroll, 'Mr. Smart's Circular Saw Mill,' p 58.

M L Read-McIlreavy, 'Peter Degraves (1788-1852)', in A G L Shaw & C M H Clark [eds], Australian Dictionary of Biography, I (Melbourne 1966), pp 302-3; Brian Carroll, The Engineers (Barton [Australian Capital Territory] 1988), pp 26-7.

Penny, *Tasmanian Forestry*, p 40.

Rachel Roxburgh & Douglass Baglin, *Colonial Farm Buildings of New South Wales* (Rigby, Adelaide 1978), p 41.

An advertisement of 1817 mentions a water mill in Hobart: *Hobart Town Gazette*, II, 36 (1 February 1817), p 1. The first windmill opened shortly afterwards on Robert Nash's property at Pitt Water, followed by another built by William and Nathaniel Lucas at Port Dalrymple, near Launceston: ibid, 37 (8 February 1817), p 2; II, 44 (29 March 1817), p 2; 51 (27 May 1817), p 2. In March it was reported that Arnold Fisk had 'at enormous expense' established a flour mill at Wellington Bridge, Hobart: ibid, 41 (8 March 1817), p 1. In about 1821 William Thornley constructed a small undershot mill at his property on the Clyde: William Thornley [ed J S Mills], *The Adventures of an Emigrant in Van Diemen's Land* (Adelaide 1973 [1840s]), p 59. In the 1840s Captain Hepburn at Smeaton, Victoria, had built his own water mill, and his neighbour Alfred Joyce, after experimenting with wind power, built a mill powered by an undershot waterwheel, notwithstanding the fact that it had to be dismantled each season to prevent it being destroyed when the creek was in flood. In turn Joyce's neighbour Benjamin Bucknall, who was more fortunately placed at a fall in the creek, built an overshot wheel housed in a permanent mill house. Alfred Joyce [ed G F James], *A Homestead History* (2nd ed,

as well, but rarely used in this way. Thomas Hall describes the complicated plans that led in the 1850s to the construction of a water powered sawmill on the Killarney cattle station near Warwick, Queensland, which required the building of a dam and the construction of machinery powerful enough to operate four large circular saws. Upon its completion the ready availability of sawn timber stimulated a demand for new houses in Warwick: another mill was established on Rosella Creek, not far way, and then after 1862 John Affleck of the Killarney Mill established a steam mill on the Upper Swan Creek.⁹³

The story of watermills being superseded by steam was to be a universal one, though the exact date in individual cases was dependent upon the sufficiency of the water power, the availability of fuel, and the proximity of the market. The first steam sawmill in Australia was projected by the accomplished engineer, John Dickson, but did not come to fruition. Dickson reached Sydney in 1813 with tools, turning lathes, and a steam engine to work his mill. The engine was set up on Cockle Bay (Darling Harbour) and was working in 1815, but used only for grinding flour, not for sawmilling as intended. ⁹⁴ In 1820 W C Wentworth commented that someone who would take out to Sydney a six or eight horsepower steam engine and machinery for making boards would have a fair chance of success. ⁹⁵

It was also in about 1820 that a design for a prefabricated sawmill for Van Diemen's Land was prepared, apparently by the engineer Marc Brunel, but it is not clear what became of it, or how it was to have been powered. By 1833 the Van Diemen's Land Company had steam machinery at Circular Head driving a flour and sawmill, with both vertical and circular saws, and by 1837 there were steam sawmills operating in Launceston. These pioneers seem to be forgotten by J C Penny, who names the first sawmill in the north as that of Cummings, Raymond & Co on the River Don in 1852, whereas in fact this mill seems to have been opened in 1854, burnt down in 1855, then

Melbourne 1949 [1942]), pp 69-72. There is no indication that any of these were used for timber milling.

G P E Walsh, 'John Dickson (1714-1843)', in A G L Shaw & C M H Clark [eds], Australian Dictionary of Biography, I (Melbourne 1960), p 306.

Cox & Freeland, *Rude Timber Buildings*, p 37, n 5, quoting W C Wentworth, 1820.

Thomas Horton & Kenneth Morris, *The Andersons of Western Port* (Bass [Victoria] 1983), p 38, citing Records of the Van Diemen's Land Company at Circular Head, Archives Office of Tasmania.

A R J Billman, 'The Timber Vernacular' (BArch, Deakin University 1992), p 165, citing John Dargavel [ed], *Sawing, Selling and Sons* ([Centre for Resource and Environmental Studies] Canberra 1988), p 19.

Penny, *Tasmanian Forestry,* p 39.

Thomas Hall, *The Early History of the Warwick District and Pioneers of the Darling Downs* (Toowoomba [Queensland] 1988 [Toowoomba, no date (?1920s)]), pp 124-6

Terence Lane of the National Gallery of Victoria reported a meeting in 1988 with the English art critic, Edward Lucie-Smith, who held four of five drawings for this mill, which he wished to sell. They were said to 'have some connection with the British engineer, Brunel', which, given the date, must mean Mark Brunel rather than his more famous son. I wrote to Smith seeking information with a view to making an offer, but received no reply.

rebuilt.¹⁰⁰ It was therefore preceded even by William Moore's Ilfracombe Sawmill on the Tamar, near Beaconsfield, built in 1853,¹⁰¹ and by the Romney Sawmill on the Mersey. which opened that year with one circular and six 'perpendicular' saws.¹⁰²

On the settlement of Adelaide the South Australian Company engaged Henry Mildred to buy the necessary apparatus in the north of England for a steam saw and corn mill, as well as a shipyard and patent slip. He reached Kangaroo Island on 22 April 1837 and after some delay part of the plant was moved to Adelaide. Here the engine and mills were put up, and were generally known as the 'Company's mill'. 103 In 1839 a handbook for South Australian emigrants was advertising 'sawing machines'. 104 In about 1847-9 G M Stephen established a steam sawmill with a sixty horsepower [35 kW] engine at Cox's Creek, though the iron smelter which was intended to go with it never eventuated. 105 In November 1849 the brothers Robert and John Shepherdson opened a portable sawmill in the redgum country at Littlehampton, near Mount Barker. Robert is said to have designed the mill himself and constructed it using forgings and castings from C & H Wyatt's foundry in Adelaide. 106 Robert moved the mill to Penola in 1862, then soon afterwards to Springhill, Victoria, where he continued to operate and move it, in the vicinity of Springhill, Trentham, Kyneton and Tylden. 107

More often than not the type of saw used in any particular mill is unlnown. In Sydney the first steam powered saw is claimed to have been in operation by October 1838, and it is said to have been a vertical reciprocating saw which could turn out true pieces in a hundredth the time of the pit sawyers. In 1842 a circular saw, described as being twice as fast as its predecessor, went into operation in Sydney. In 1850 the Royal Engineers brought three circular saws for use at the Convict Establishment in Fremantle, and one at least of these was driven off a wheel powered by six convicts - probably the traditional treadmill. A steam sawmill was built at Brisbane Water, New

James Fenton, Bush Life in Tasmania Fifty Years Ago (London 1891), pp 106-7.

Penny, *Tasmanian Forestry*, p 39.

Fenton, Bush Life in Tasmania, p 85.

J W Bull, *Early Experiences of Life in South Australia* (London 1884), 24. Henry Capper, *Capper's South Australia* (3rd ed, London 1839 [1837]), advertisements

Douglas Pike, *Paradise of Dissent* (Melbourne 1967 [1957]), p 358, ref *South Australian Gazette and Colonial Register*, 25 September 1847; *South Australian Register*, 10 October 1849.

David Mack, *The Shepherdsons: Timber Milling in Australia 1849-1984* (Camden Park [South Australia] 1986), p 2.

Mack, The Shepherdsons, p 3.

Cox & Freeland, *Rude Timber Buildings*, p 37, n 4, quoting the *Sydney Herald*, 31 October 1838. They presumably refer to a mention on p 1 of 'Dickson's Steam Mills', though these, as we have seen, were apparently flour rather than sawmills. In the *Herald* of 26 October 1838 there is an advertisement for W G Card & Co's Australian Saw Mills in Bathurst Street, though it is not stated that these are steam powered. Where Cox and Freeland get their information about the type of saw is unclear.

Cox & Freeland, Rude Timber Buildings, p 37, n 6.

R M Campbell, 'Building the Fremantle Convict Establishment' (PhD submission. University of Western Australia, 2010), pp 56-7.

South Wales, in about 1853-4 under the supervision of the engineer H C Mais. 111 John Young, while constructing the Sydney Exhibition Building in 1878-9, rented out from Hudson Brothers and operated on the site what is referred to as a sawmill, though it seems to have been much more. It included two circular saws, a cylinder planing machine, a universal boring machine, a four-sided moulding machine, a cross-cut saw bench, and a hand saw [?band saw] for circular cutting. 112 In 1879 the 'Patent Guide-Lined Circular Saw', which at 885/8 inches [2.251 m] diameter was the largest circular saw ever made in Britain, was shown at the Sydney Exhibition by Taylor Brothers of Sheffield. 113

Two steam flour and sawmills seem to have opened in Melbourne in 1841, and there were several by 1845. 114 It seems that sawmills were a first concentrated in the main port towns, often at the wharves themselves, and usually dealt with imported timber. Sometimes they dealt with other things as well: in 1853 E B Hurst advertised his steam sawmills in Bourke Street, Melbourne, where he would also grind coffee, pepper and spices, and grind or crush maize. 115 But during the 1850s sawmills opened up in the inland, reflecting the increasing use of indigenous timbers. In 1844 Western Australia's first steam sawmill began operations at Guildford. 116 In Brisbane William Pettigrew opened the first steam sawmill on the corner of William and Margaret Streets, by Queens Wharf, in 1853, 117 with a capacity of 75,000 super feet [17.7 m³] per day. 118 In the early 1860s Pettigrew established at Dundathu on the Mary River, eleven kilometres below Maryborough, a mill which was soon to produce 3.3 million super feet [7800 m³] of timber per year, at an annual profit of £15,000. 119 By 1865 there were nineteen sawmills in Queensland as a whole, and thirty-one by 1868. 120 By 1890 a single mill, J D Campbell's at Breakfast Creek, was employing up to four hundred workers. 121

The 'ribbon or endless saw', later known as the band saw, was patented in Britain by William Newberry in 1808, and is said to have been independently

Sally O'Neill, 'Henry Coathupe Mais (1827-1916)', in Bede Nairn et al [eds], *Australian Dictionary of Biography*, V (Melbourne 1974), p 200.

Sydney International Exhibition 1879, Official Catalogue of the British Section (London 1879), p 65.

Auction Mart, 21 June 1853, ?p.

Jenny Mills, *The Timber People* (Perth 1986), p 67.

Donald Watson, *The Queensland House* (report, Brisbane 1981), p 4.3.

Dornan & Cryle, *The Petrie Family*, p 102.

Watson, *The Queensland House*, p 5.3.

Peter Proudfoot, 'Management and Materials: the Genius of John Young', in Peter Proudfoot, Roslyn Maguire & Robert Freestone [eds], *Colonial City Global City: Sydney's International Exhibition 1879* (Darlinghurst [New South Wales] 2000), p 69, note 17, ref *Sydney Mail*, 8 March 1879.

Miles Lewis, 'Tradition and Innovation in Victorian Building' (3 vols, PhD, University of Melbourne 1972), I, p 137; III, pp 557-8.

Dimity Dornan & Denis Cryle, *The Petrie Family: Building Colonial Brisbane* (St Lucia [Queensland] 1992), p 115.

Dornan & Cryle, *The Petrie Family*, p 169, ref *History of Brisbane*, p 5.

reinvented in the US soon afterwards, 122 but seems not to have been seriously taken up until the 1850s, 123 and we have no indication of when it reached Australia. Otherwise the fundamentals of sawmilling remained unchanged for about a century and a half. The Donnelly River Timber Mill at Nannup, three hundred kilometres south of Perth, was opened in 1949, and in 2005 was reported to be Western Australia's last and most complete example. It had employed up to 150 men, on eight saw benches powered by a horizontally mounted Robey steam engine, and could break down logs up to two metres diameter into slices as slim as 8 mm (used for fruit boxes). 124

e. woodworking machinery

The development of woodworking machinery effectively began with the machines patented by Samuel Bentham in April 1793 for shipbuilding purposes, 125 amongst them a planing machine, together with other developments by Joseph Bramah, Henry Maudslay and Marc Brunel (whose sawmill for Van Diemen's Land has been mentioned). Bramah's machine, patented in 1802 as 'Machinery for producing straight, parallel, and smooth surfaces of wood and other materials', was used at the Woolwich Arsenal for at least sixty years. Maudslay had worked with Bramah, but subsequently went on to develop his own machines. 126 In 1791 Bentham had used a cruciform bit to cut mortices with rounded ends, which then had to be finished with a chisel, but in 1807 in association with Maudslay he invented a machine using a chisel with a reciprocating motion of four hundred strokes a minute, to cut a square hole. 127 The claim that Marc Brunel first introduced mechanisation at the Royal Naval Dockyards, after approaching Bentham in 1801, in his capacity as Inspector-General of Naval Works, is false, for what he in fact devised was was the first suite of machinery for the specific purpose of manufacturing ships' blocks, which came into operation in 1807. 128 In fact Brunel's mortising machine for pulley blocks survives from this period, ¹²⁹ though this is a matter of no concern to us here.

Rosenberg, 'America's Rise', p 47, citing *Niles Weekly Register*, 27 March 1819; 28 September 1833; Satoh, *Building in Britain*, pp 136, 137.

R S Burn, *Modern Building and Architecture* (London, no date [c 1870]), p 192.

Tony Moulds on the Engineering Heritage web site, 10 January 2004.

Robert Mallet, 'Machines for Direct Use - Engineering Tools', in Robert Mallet [ed], *The Record of the 1862 International Exhibition* (Glasgow 1862), p 294.

Mallet, 'Machines for Direct Use', pp 293-4.

Satoh, Building in Britain, p 143, ref Holtzapffel, Turning and Mechanical Manipulation, II, pp 505-6; M P Bale, Woodworking Machinery (London 1894), pp 148-151.

Abraham Rees, *The Cyclopædia, or Universal Dictionary of Arts, Sciences and Literature* (39 vols + 6 of plates, Longman, Hurst, Rees, Orme, & Brown, London 1819), XXII, sv 'Machinery for Manufacturing Ships' Blocks', p 1. This is confirmed by K R Gilbert, *The Portsmouth Blockmaking Machinery* (London 1965), p 35-40, though he oddly refers to the arttycle on 'Machinery' at the end of volume XXVIII of Rees, rather than the correct one, and attributes the authorship to John Farey, on grounds which are not apparent.

Barry Russell, *Building Systems, Industrialization, and Architecture* (London 1981), pp 36-7.

This machinery for shipbuilding had little impact in general joinery. 130 The United States at first lagged behind Britain and there were few technical developments until the 1820s. The planing machine was not much used there before 1828, 131 when William Woodworth patented his version. 132 The higher cost of labour in the United States encouraged the adoption of machinery in which 'more attention [was] paid to economy of time and labour, and to the production of rapid results with the last possible expenditure, than to great durability of finish' and which did not exhibit 'elegance of workmanship' so much as 'boldness of design'. This American machinery, unlike that in England, had permeated the trade down to the smallest workshops, and by 1851 British patents had been taken out by William Furness of Liverpool, who was importing the American machinery and who displayed some of it at the Great Exhibition. This included a foot-operated mortising machine, a tenoning machine to be worked by hand or power, and power-driven mortising, planing, moulding and sash-making machines. They exhibited 'great ingenuity, simplicity, and fitness fore the purpose', and were mostly framed in wood, not only because it was cheaper, but because it was less likely to bruise highly finished work. 133 Furness claimed that his machines had been used in the construction of St George's Hall, Liverpool, the Houses of Parliament at Westminster, and the Crystal Palace itself. 134 By 1853 he was advertising that his machines were in general use throughout the United Kingdom for planing, squaring up, moulding, tenoning, mortising, grooving, rebating, sawing and boring. 135

In 1848 C B Rogers & Company of Norwich, Connecticut, brought into production what has been claimed to be the first successful moulding machine, the but Australia seems at first to have relied entirely upon British machinery. In 1846 milling machines appeared in Sydney, including one which could run four faces of a moulding simultaneously (like that later used by Young), and, operating with two men and a boy, could do the work of 250 joiners. In 1846 W H Burnett of London was promoting a new moulding machine on the basis that he would sell only two in Sydney and one in Melbourne, the but in Melbourne at least, a moulding mill was established only in early 1854 by James Swinbourne (later Bleasby, Swinbourne & Co). Later that year, however, W & J Gripe of the City Saw Mills showed at the

Mallet, 'Machines for Direct Use', pp 293-4.

J H Englund, 'An Outline of the Development of Wood Moulding Machinery', *APT Bulletin*, X, 4 (1978), pp 20-21.

Rosenberg, 'America's Rise', p 48.

London, Great Exhibition of the Works of Industry of all Nations, 1851, Official Descriptive and Illustrated Catalogue (3 vols, London 1851), I, p 298; ibid, Reports by the Juries on the Subjects in the Thirty Classes into which the Exhibition was divided (London 1852), p 201.

Great Exhibition, *Catalogue*, I, advertisements p 47.

Builder (London), XI, 539 (4 June 1853), p 367.

Englund, 'Wood Moulding Machinery', p 23.

Cox & Freeland, Rude Timber Buildings, p 37, n 7.

Port Phillip Herald, 12 November 1846.

Isaac Selby, *The Old Pioneers' Memorial History of Melbourne* (Melbourne 1924), p 144; C B Mayes, *The Victorian Contractors' and Builders' Price-Book* (Melbourne 1859), p xliv. By 1855 there were six mills: Lewis, op cit, I, p 142.

Melbourne Exhibition a moulding machine which had actually been made in the colony, as well as some of the mouldings made by it. By 1855 there were at least six moulding mills in Melbourne, and in that year the firm of Goodlet & Smith was founded in Sydney, though it is unclear whether they were anything more than a sawmill in the first instance.

At the 1866-7 Exhibition, Briscoe and Co had also shown an imported steam-driven machine for planing, grooving, boring, moulding, tenoning and mitreing. One of the leading British makers of woodworking machinery was Samuel Worssam & Co of London, who in 1879 exhibited at Sydney:

Patent General Joiner and Combined Moulding and Planing Machine for Sawing, Tenoning, Grooving, Moulding and Planing, Mortising and Boring curved and irregular work, &c. Improved Saw-Sharpening Machine for Circular and Frame Saws. Improved Plain Band Saw Machine, for sawing curved or straight work. Improved Small Four-Cutter Moulding and Planing Machine for working all four sides of mouldings at one operation. Improved Hand Mortising and Boring Machine for Joiners' Work, Patent Self-Acting Rope Feed Circular Bench, with Carriages and Rails.

Overseas, the advent of such machines had no immediate effect upon the design of joinery and components, for, apart from speed and efficiency, their capacities were similar to those of manual operators. So far as the US was concerned the result was a greater use of mouldings, rather than any stylistic innovation, ¹⁴⁵ and the same was doubtless true in the Australian colonies. In the 1890s the architect L J Flannagan was simply citing catalogue numbers of mouldings on his working drawings, as with 'Jas Moore 446', 'Jas Moore 422', 'A Kerr No 184', and 'A Kerr 510'.

Planing machines seem to have been entirely imported to Australia until 1880. In addition to Furness's exhibits in 1851 there was an American planing machine by J P Woodbury of Boston which was noticed favourably by the jurors, 147 as well as a French one by Sautreuil of Fécamp. 148 But the Melbourne International Exhibition of 1880 the Atlas Co of Engineers showed a moulding, planing, tonguing and grooving machine, presumably of their own manufacture, 149 and in the 1880s a South Australian called Rendon invented a planing and moulding machine which was said to be more effective than any then known in the colonies.

Melbourne Exhibition 1854, Official Catalogue (Melbourne 1854), p 15.

Lewis, 'Victorian Building', I, p 141-2.

Australasian Builder & Contractor's News, 28 May 1887, pp 37.

¹⁴³ Intercolonial Exhibition 1866-67, Official Record, p 39.

Sydney Exhibition 1879, *Catalogue of British Section*, p 241. Worssam's had shown various machines at the 1862 Exhibition: Mallet, 'Machines for Direct Use', p 314

Englund, 'Wood Moulding Machinery', p 25.

Flannagan photographs, SLV, door and window details and amended plan of bathroom for the architect's own house, Thanet and Ray Streets, Malvern, 1890-1.

Great Exhibition, Catalogue, III, pp 1463-4; ibid, Reports by the Juries, pp 201, 318.

Great Exhibition, *Catalogue*, III, p 1246.

Melbourne Exhibition 1880, Catalogue, p 50.

Mortising machines, although they began with that developed by Bentham and Maudslay in 1807, came into general around 1850. In particular, a mortising machine was invented by the American engineer J A Fay in about 1840, ¹⁵⁰ patented in England by William Furness of Liverpool, and was in use at E T Bellhouse's works at Manchester by 1849. ¹⁵¹ This was one of the machines shown by Furness at the Great Exhibition, and was claimed to be suitable for hard as well as softwood. ¹⁵²

At the Melbourne Exhibition of 1854, Joseph Hill of Emerald Hill, Melbourne, displayed a 'Coulson's Patent Mortising Machine, with 6 chisels in various sizes and 2 spanners, for altering the machine at convenience. This was an imported machine, only one of at least four types which had become available in England after Furness's, and also said to be able to mortise hardwood as well as soft. It was the registered design of William Coulson of York, dating from January 1852. By 1858 another type, Hugh's patent, had been imported by the Collins Street agent G H Pettigrew, and at the 1866-7 Exhibition, Briscoe and Company of Melbourne showed a mortising machine of unspecified origin. In 1870 Greville & Co of Sydney showed two Merrett & Gibbs patent boring and mortising machines, one with a wooden and one with an iron frame, though these were more specifically intended for fence posts. A mortising machine branded by T Robinson & Sons of Rochdale survives art the Launceston Railway Workshops, now part of the Queen Victoria Museum.

Fretwork, which provided a cheap alternative to the elaborately modelled bargeboards of the picturesque Gothic house, came into vogue in Britain in the years following the Paris Exhibition of 1867, and became especially popular in the 1880s, when it was produced using fret machines from the United States. The situation was probably just the same in Australia.

Mechanical woodcarving had made an appearance in Britain in the 1840s, with machines by Pratt and Jordan, which were also used to carve stone, 161

Manchester Examiner and Times, I, 98 (10 October 1849), p 4.

¹⁵⁰ Satoh, *Building in Britain*, p 143.

Builder (London), XI, 565 (3 December 1853), p 739: the advertisement includes a small illustration.

¹⁵³ Melbourne Exhibition 1854, *Catalogue*, p 19.

Builder, X, 396 (19 July 1852), p 398. See also V, 221 (1 May 1847), p 210, for Jones's patent; VII, 335 (7 July 1849) for Mortimer's patent; and 525 (28 February 1853), p 144, for Worssam & Co's.

Builder, XI, 550 (20 August 1853), p 543: the advertisement includes an illustration of the machine.

Victoria Industrial Society, *Catalogue of the Eighth Annual Exhibition* (Melbourne 1888), p 28.

Intercolonial Exhibition, 1866-67, Official Record, p 39.

The Industrial Progress of New South Wales (Sydney 1871), p 113.

Inspected 2008.

Louw, 'The Mechanisation of Architectural Woodwork in Britain, Part IV', pp 20-21.

Satoh, *Building in Britain*, pp 121-3, 142, & 156 note 25. T B Jordan's machine received the medal of the Society of Arts in 1847, and is described and illustrated in Charles Tomlinson [ed], *Cyclopædia of Useful Arts & Manufactures* (in parts, London c 1852), II, pp 346-7 (sv Carving by Machinery).

but only roughed the work out, leaving it to be finished by hand. Another machine, patented by Irving, was used at a Pimlico factory owned by Pratt, under the supervision of R W Billings, and consisted of a simple drill on a movable arm. It too was used for both wood and stone carving, powered by steam or by a hand-turned wheel, with the work on a movable table. It was later used at Lambeth in association with Jordan's machine. The Jordan & Co machine at the Great Exhibition used a whole series of drills, pointed from a model, and one of the products shown was a gothic oak screen bearing dead game, foliage &c. This machine was exhibited unaltered in 1862, and achieved considerable commercial success in the 1860s and 1870s, though late in the century, there was a revival of activity based largely upon American machines.

In 1866 William Williams exhibited at Melbourne a machine intended for turning axe handles, but in principle capable of much wider application: 166

A model of the article to be produced is placed in one portion of the machine, and a piece of wood roughly shaped, and of sufficient bulk to enable an article of similar size and shape to be manufactured from it, is introduced into another part of the machine. By an ingenious arrangement of mechanism, the model is strictly copied, and its form reproduced in the rough timber placed in apparatus.

The machine had already been in use in Melbourne for some years, and there is no reason to suppose that it was a local invention, so it was probably one of the overseas models such as Jordan's.

Subsequently Marles and Butt of England developed what was described as the first effective wood carving machine, the 'Marbut', which was manufactured for them by the Ransome Engineering Works and patented all over the world. This was claimed to produce work equal to anything that could be done by hand. A Melbourne man, A Holloway, visited England and obtained patent rights for Australia, then established the Australian Marbut Carving Company Limited, of Queen Street, Melbourne. Much of the production consisted on non-architectural goods such as furniture and picture frames, but it also included skirtings, architraves and chair rails. 169

C J Richardson, The Englishman's House from a Cottage to a Mansion (London 1870), pp 278-9.

Great Exhibition, *Juries' Reports*, p 550. Mallet, 'Machines for Direct Use', p 314.

Louw, 'The Mechanisation of Architectural Woodwork in Britain, Part IV', p 20.

Intercolonial Exhibition 1866-67, Official Record, p 368.

James Smith [ed], *The Cyclopedia of Victoria* (3 vols, Melbourne, 1903, 1904, 1905), II, p 159

Louw, 'The Mechanisation of Architectural Woodwork in Britain, Part IV', p 28, quoting the *Illustrated Carpenter and Builder,* Supplement, 27 July 1900, p 4. According to Louw the machine was not invented by Marles and Butt, but by a joiner, H Marbut, employed by Allen Ransome & Co.

Smith, Cyclopedia of Victoria, II, p 159.

f. seasoning

The degree of shrinkage in Australian timber is such as to make thorough seasoning very desirable. In 1820 Patrick Riley of Newcastle advocated felling the trees only in the winter months of May, June and July, cutting the timber into planks, and exposing it to the weather. How long it was to be thus seasoned is unclear, but Riley did say that insufficient time was being allowed at Newcastle because of the level of consumption at 'Head Quarters' [Sydney]. It seems improbable that the average timber cutter would be prepared to confine his activities to three months of the year, quite apart from the pressure to skimp on the seasoning. In 1877 Mayes prescribed the timber-getting season as being March to September. The timber was to be split or sawn, and then stacked in the shade in such a manner as to be well ventilated. The problem was that the ends opened up in the process of drying, and often they were bolted together to ameliorate this effect. There could be no question of sealing the ends with tar, for the whole purpose was to let the sap evaporate, and such treatment would cause rot. 171

Salt water seasoning was a traditional method, mentioned by Pliny and advocated by John Evelyn. Some, however, argued that fresh water was better, and there was also an intermediate school which favoured salt water for ships' timbers and fresh water building timbers. Captain Henry Waterhouse reported in 1802 that logs which were cut down at Sydney in 1788 to clear the land for settlement, and rolled into the water, had been taken up years later and found to be as sound as they began. This was of course fortuitous, and deliberate attempts at salt water seasoning come later. At Alexander Berry's 'Coolangatta' estate at Shoalhaven, in the 1820s, his builders were required to throw the planks for the barn floor

into the canal and allow it to remain for a fortnight - this will not only extract the sap and render it less liable to shrink after it has again become dry - but the salt will prevent it from being attacked by the worm. ¹⁷⁴

In Western Australia jarrah logs were left in sea water for a few weeks, then drawn up onto the beach and covered with a few inches of seaweed, their ends protected from the sun. They were then left for a number of months to season, cut into boards 180 mm wide, stacked to allow air to pass around them, and left five or six months longer before use. ¹⁷⁵

Evidence of Patrick Riley [undated but c 1820], in John Ritchie [ed] *The Evidence of the Bigge Reports* (2 vols, Melbourne 1971), I, p 113.

Charles Mayes, *The Australian Builders' Price-Book* [3rd ed, Melbourne 1877], p 62.

T A Britton, A Treatise on Dry Rot in Timber (London 1885), pp 73-6.

Captain Waterhouse, 'Memorandum on the Timber of New South Wales', 2 March 1802, Public Record Office, London, CO 201/1, quoted in Daniel Paine [ed R J B Knight & Alan Frost], *The Journal of Daniel Paine 1794-1797* (Sydney 1987), p 78.

Papers of Alexander Berry, volume 5, 16 August 1824, quoted by Rachel Roxburgh & Douglass Baglin, *Colonial Farm Buildings of New South Wales* (Adelaide 1978), p 32.

Britton, *Dry Rot*, p 115.

An important innovation in the later nineteenth century was the introduction of seasoning on the Reiser system, which made a number of local timbers viable for joinery and finishing. Reiser was a Swiss who was reportedly on Maria Island, Tasmania, in 1887. In 1888 he was living in Melbourne, and obtained a patent for improvements in apparatus for seasoning timber, ¹⁷⁶ and soon afterwards he and A D Hunter sought and gained government financial assistance, ¹⁷⁷ probably for what was at first called the Melbourne Reiser Timber Seasoning Syndicate. By now the sawmiller R A Robertson was involved, for he told the Commissioner for Customs in June 1889 that he was representing a Swiss method of seasoning timber, and that if a duty were to be levied on imported wood he would be able to produce timber from colonial woods just as good as the imports. ¹⁷⁸

In 1892 the Australian Seasoned Timber Company Limited was formed to unite the interests of the Comet Mills, the Melbourne Reiser Timber Seasoning Syndicate and, apparently, the Victorian Terra Cotta Company, makers of terra cotta lumber (as discussed below). The principals included Robertson, Hunter, and presumably Reiser himself, and a mill was established at Wandong on the North-Eastern Railway Line, near Kilmore. An early instance of the use of the process is the court house at Bairnsdale, Victoria, for which 'samples of mountain ash of beautiful grain and colour, and to all appearances perfectly seasoned', were submitted in 1894 by the Australian Seasoned Timber Company.

Neither the seasoning nor the terra cotta lumber business was viable during the depression of the 1890s, the latter being kept open for only three months in the second half of 1896, and apparently entirely inoperative in 1898 and 1899. But the sawmill expanded, and despatched a shipment of wooden paving blocks to London, from which a major contract was expected to follow. Apparently this did not eventuate, and in any case the Comet Mill was burnt down in 1900, and it was decided in 1902-3 to move the business to Western Australia and to liquidate the Australian Seasoned Timber Company. 183

After World War I the Melbourne firm of Cuming, Smith & Co established a wood distillation and timber seasoning works near Warburton. The seasoning was done by what they described as 'the moist air method', in which the timber, after some preliminary drying in the open air, was placed for a week or more in a kiln with the humidity controlled to suit the wood being treated. The heat was supplied by steam-filled pipes, over which passed the air entering the kiln, and this seems to be but a little way short of the system of

Australasian Builder & Contractor's News, 29 December 1888, p 600.

G S Perrin, *Australian Timbers* (Sydney 1893), p 26.

Australasian Builder & Contractor's News, 29 June 1889, p 606.

J W Payne, *Pretty Sally's Hill* (Kilmore [Victoria] 1981), pp 56-7.

Perrin, *Australian Timbers*, p 26.

Bairnsdale Advertiser, 26 April 1894.

Colin Harvey, *Wandong Wanderer* (tour notes of the Light Railway Research Society of Australia Inc, 1981, unpaginated).

Payne, *Pretty Sally's Hill,* pp 57-8.

Cuming, Smith & Co Pty Ltd, *Our Forest Industries* (Melbourne, no date, unpaginated).

steam drying in kilns which was introduced in Western Australia. Jarrah had reputation for cracking, and did this even after a periods of open air seasoning at the mill.

The American visitor, H D Tiemann of the United States Forest Service. 185 developed his 'water spray humidity regulated kiln' for drying jarrah, in which the first rapid seasoning tests in the state were begun in 1918. 186 Timber was stacked in the kiln and dried using steam heated coils, and the air was humidified as it passed through water was sprayed within chambers on either side. When the drying was proceeding too rapidly, and traces of surface cracking began to appear, live steam was introduced, and by this means the moisture content was kept consistent throughout he plank during drying. The kilns at Yarloop were modified in accordance with this principle in 1921, 187 and Stanley Clarke, the officer in charge of seasoning investigations, promoted the concept. The kilns were sometimes referred to by his name, as when the Adelaide Timber Company of Western Australia constructed a battery of six 'S.A. Clarke' steam kilns in 1925-6, to meet a demand from South Australian and Victorian dealers, mainly for 5 x 1 inch [125 x 25 mm] flooring boards. 188 By 1932 all commercial kilns in Western Australia save one were of this type, though those of the Adelaide Timber Company closed permanently in about 1930 because of the economic depression. In the meantime a range of modifications and developments had given rise to at least half a dozen local patents. 190

In Victoria the method used by Cuming Smith remained adequate, and it was streamlined when P V Christensen of the firm of Christensen & Saxton, Moe, developed what became known as the 'Christensen truck', which eliminated double handling of the timber. The pieces which were being initially air-dried were placed on bolsters which rested in turn on sleds or foundations built over a set of rails, and the stack was of the size which was required to charge the kiln. When the time came to transfer the wood to the kiln the truck could be slid along the rails under the stack, lift it, and shift it as required. ¹⁹¹

g. preservative treatments

The earliest preservative treatment for local timber was to char that part of it that was set in the ground. David Burn, writing of Van Diemen's Land in

Council for Scientific and Industrial Research, Division of Forest Products, *Types of Timber Seasoning Kiln* [trade circular no 17] (Melbourne 1933), p 10.

S A Clarke, *The Seasoning of Western Australian Hardwoods* (Perth 1927), p 34.

Staples, *They Made Their Destiny*, p 331.

Clarke, Seasoning of Western Australian Hardwoods, pp 34-42; Staples, They Made Their Destiny, p 331.

Mack, The Shepherdsons, p 39.

A J Gibson, A Forest Products Laboratory for Australia [Council for Scientific and Industrial Research pamphlet no 9] (Melbourne 1928), p 11.

Combined Air and Kiln Seasoning: Handling by Means of the Christensen Truck [Trade Circular no 12 of the Council for Scientific and Industrial Research, Division of Forest Products] (Melbourne 1932), passim.

about 1840, said that this would enable fence posts to last fourteen or fifteen years. For items like telegraph posts charring remained a common practice through the nineteenth and most of the twentieth century. Charring had been one of the many treatments described in Neeve's *Builder's Dictionary* in 1736, which reported its use in Britain, Germany and Venice. Others, most of which persisted into the nieteemth century in some form or other, included soaking the timber in water (to bremove the sap), burying it in the ground, daubing it with cow dung, smoking it, and painting it with linseed oil, pitch, tar (to which the Dutch would add shellgrit), 'oil of smoak', vegetable oil, or yellow sulphur. 193

Chemical preservative treatments for timber were not so common in Australia as in Britain because hardwoods would not absorb chemicals to any significant extent, but of course there were primitive processes used at times. One of the earliest in Britain was J H Kyan's process, which involved soaking the wood in corrosive sublimate (mercuric bichloride). In 1828 Kyan obtained permission for his system to be tested at the government dockyards, and a specimen was immersed in a pit at Woolwich Dockyard for three years, 'subject to foul air and fungus mould', then in a further test in 1831 nine specimens were built into various structures susceptible to rot, and survived, while nine untreated pieces did not. 194 In March 1832 Kyan took out a patent, 195 the rights to which he transferred to a company which put the process into commercial operation. The company established 'stations of tanks' at Pimlico, Rotherhithe and City Road Basin, London, for the treatment of timber, canvas and cordage, as well as advertising its willingness to grant licences to others. 196 One such licensee was the Anti-Dry-Rot Company. 197 Henry Manning, the London prefabricator, used the process, and the timbers of his Quaker Meeting House, sent to Adelaide in 1839, were Kyanised. 198 Not only that, but the building was placed on display for a fortnight 'at Kyan's anti-dry-rot tanks' at the West India Docks. 199

Another approach was to coat the timber in an impervious layer of 'Jeffery's marine glue', a combination of 'elastic gum with non-elastic'. The components - as revealed only at a later date - were:

¹⁹² David Burn, *A Picture of Van Diemen's Land* (Hobart 1973 [1840-41]), p 182.

Richard Neve, *The City and Country Purchaser, and Builder's Dictionary: or the Compleat Builders Guide*, London 1703, sv Timber.

Mechanic's Magazine, XVIII, 489 (22 December 1832), p 189; George Birkbeck, The Preservation of Timber by Kyan's Patent (London, no date [c 1835]).

British patent no 6253 to John Howard Kyan, 31 March 1832, for preserving certain vegetable substances from decay. This was followed by no 6309 of 22 September 1832 for preserving paper, canvas, cloth and cordage for ships and other purposes, also the raw materials, as hemp, flax or cotton, of which the said might be made.

Advertisement appended to Birkbeck, *The Preservation of Timber*.

Information, 2005, from Stephen Massil, Librarian, Sir John Soane's Museum, London, from a prospectus held by the library.

Herbert Stock & Jenny Stock, 'Application for Inclusion of the Adelaide Meeting House on the National Heritage List: Supporting Information' (typescript, Religious Society of Friends (Quakers) Adelaide Meeting Inc., Adelaide 2006), p 24.

South Australian Record, 10 July 1839, quoted in Stock & Stock, Adelaide Meeting House'. p 8.

Alfred Jeffery, *Notes on the Marine Glue* (London 1843), pp 5-6.

1 part caoutchouc
2 parts asphaltum
12 parts undistilled coal tar.²⁰¹

Jeffery glued blocks of wood together and tested the force required to pull them apart, and he sank coated blocks in Portsmouth Harbour, where they survived for twenty-three months without apparent ill-effect.²⁰² He was unsuccessful in his efforts to get the glue adopted by the Royal Navy at this stage, but his glues are made to the present day.²⁰³

During the 1840s there was a great deal of attention given in England to preservative treatments for timber, spurred on especially by the demand for railway sleepers. John Bethell's process, patented in 1838, is the most relevant to later Australian developments. It involved impregnating the wood with oil of tar [creosote] and pyrolignite of iron [iron acetate]. Creosote, or kreosote as it was first known, was a discovery of Baron von Reichenbach, obtained by distilling tar in metallic vessel, and it had been used on timber since at least 1756 by Hales, Maconochie & Lukin, but it was Bethell who developed the system of pressure impregnation. In 1886 a creosote plant was established in New Zealand, at Woodend on the Bluff-Invercargill Railway, capable of handling timber up to 19.5 metres long. It immediately obtained a contract to process 150,000 sleepers.

Sir William Burnett's process, also dating from 1838, used zinc chloride which, when deposited in the timber, was supposed to harden it and to form a permanent compound which could never be leached out. There were many preservative works in the country, but by 1853 Durrand's Bonded and Sufferance Wharf at Rotherhithe had particular connections with the foreign and colonial trade because it could import and re-export Baltic and other timbers without incurring British duties. By 1853 it was equipped for carrying out Bethell's, Payne's, Burnett's and Margery's processes. All were supposed to be preservative, and Bethell's also to have some fireproofing value.

Raimund Hoffer [translated W T Brannt], *A Practical Treatise on Caoutchouc and Gutta Percha* (Philadelphia 1883), p 140.

Jeffery, Notes on the Marine Glue, passim.

William G Jeffery, a distant relative, has informed me by email of 28 February and 12 March 2006 that Alfred Jeffery appeared in the 1861 census as a manufacturer of glue, living in London, and as a 'manufacturer' in 1871, but by 1891 was dead, and his widow Jane was listed as a manufacturer. I suspect that the Alfred Jeffery of these details is another generation from the original inventor. The glue made today contains benzene, which the original did not, notwithstanding the fact that this is a carcinogen.

Wyatt Papworth [ed], *The Dictionary of Architecture* (London 1853-92), svv Bethell's Patent; Creasote [*sic*]. This is here alleged to be the correct spelling, but it was spelled 'creosote' in Bethell's exhibit in 1851.

London, Great Exhibition, Catalogue, III, p 1114.

London, Great Exhibition, 1851, Reports by Juries, p 122.

Australasian Ironmonger 1 April 1886, p 2, quoting the Otago Witness.

Papworth, *Dictionary*, sv Burnettizing. See also Great Exhibition, *Official Catalogue*, I, p 196*.

²⁰⁹ Builder, XI, 526 (5 March 1853), p 160.

'Non-combustible' timber had made its appearance in Victoria by 1854, 210 but there was at first no attempt to treat the local timbers, doubtless because their structure made them far more difficult to inject, and because some were naturally very durable in any case. In June 1856 the *Australian Builder* published the first local description of a method of fireproofing timber, by steeping it for four or five days in a strong solution of alum and copper sulphate. 211 In 1874 the *Town and Country Journal* relayed an English report of a Dr Jones's patent treatment, which had been shown experimentally to protect timber and even gunpowder from fire. But the nature of the substance is not revealed, and there is no evidence of its use in Australia. 212

Following the report on fireproofing timber, in 1856, the *Australian Builder* published a summary account of the three main processes for inhibiting decay, Kyan's, Payne's and Bethell's.²¹³ Of these Kyan's process, whereby the timber was either soaked in or injected with corrosive sublimate (mercuric chloride or bichloride) was particularly expensive - notwithstanding the fact that the chemical was widely used in Australia for treating scab in sheep - and it was ousted by Burnett's process, which used much cheaper zinc chloride. Both were in fact of limited value because they precipitated soluble salts which washed out, and because they were acidic and caused corrosion in any iron fittings attached to the wood.²¹⁴ Payne's process involved the precipitation of an insoluble salt, of which there were various types, but the original version used iron sulphate and calcium chloride to precipitate calcium sulphate.²¹⁵ The process was promoted in South Australia, after which an attempt was made to set up a company in Melbourne to market it. A meeting was held in the Criterion Hotel on 24 April 1858 to consider the matter,²¹⁶ but nothing seems to have come of it.

The most effective method of injecting timber was that of James Burton, using a pressure cylinder, but that was not introduced to the Australian colonies until many decades later. Apart from simple soaking, the alternative method was that of the physician J A Boucherie of Paris, ²¹⁷ who inserted chemicals into the living tree so that they were taken up naturally. Something of the sort was done to trees in Royal Park, Melbourne, by one Léonce

Mount Alexander Mail, 15 September 1854.

Australian Builder, 17 (26 June 1856), p 138.

Town and Country Journal, 4 June 1881, p 1077.

Australian Builder, 27 (21 November 1874), p 817, quoting the Building News.

For a more detailed discussion of these treatments see Miles Lewis, 'Tradition and Innovation in Victorian Building' (3 vols, PhD, University of Melbourne 1972), II, pp 163-8. For Kyan's process see especially George Birkbeck, The Preservation of Timber on Kyan's Patent [offprint of a paper delivered to the Society of Arts, 9 December 1834] (London, no date [c1835]), passim. Birkbeck himself subsequently received a patent for a preservative method communicated to him by G Howitz: British patent no 2164 to G H Birkbeck [G Howitz], 30 July 1862.

Papworth, *Dictionary*, sv Payne's Process. See also Great Exhibition, *Official Catalogue*, I, p 208*.

²¹⁶ Argus, 27 April 1858.

London, Great Exhibition, *Catalogue*, III, p 1230.

Richards, who claimed to have patented his process of 'metallisation', ²¹⁸ but discrepancies in the reporting of this, and the absence of any patent in Richards's name or that of his agent Caspar, make it impossible to determine what was actually done.

A quite different approach was the use of silicates, which Frederick Ransome had developed in England principally as a means of preserving stone and of creating artificial stone, but also for preserving timber. Ransome's process, as well as the related ones of Dembinski and Szerelmey, have been discussed in detail in relation to stone. Richard Forrest obtained a Victorian patent in October 1861 for the preservation of materials, including timber, using 'an alkaline solution of silica, from which, after application, the alkali is extracted by means of some other mineral.'²¹⁹ A further patent in Ransome's own name in 1862 seems to overlap with Forrest's in using 'certain silicates ... in the manufacture of artificial stone and cement or plaster, and in treating timber for the purpose of preserving the same.'²²⁰ Forrest was reported to be a Melbourne merchant, and it seems possible that he was a member of the firm of Sprigg, Addison & Co of Flinders Lane, who were Ransome's Melbourne agents.

A further local patent by A C L De Lacy seems to cover similar ground, using 'certain chemical fluids and operations' for preserving wood and other materials from decay and fire, manufacturing artificial stone, &c. De Lacy was a Melbourne engineer, but it is impossible to determine whether this was in any sense his own development or whether - as seems more probable - it represents the extension of a British patent. Nor do we know whether it was put into practice locally. The patent is more concerned with the means of impregnation, using a pressure cylinder which he had patented five years earlier, and de Lacy named a number of chemicals which he would inject separately or in combination - calcium chloride, magnesium chloride, sodium silicate, aluminium sulphate, aluminium chloride, potash, creosote and fluoric acid.²²³

There is little reason to suppose that any of these treatments would be particularly successful, and no evidence to suggest that they were. Coating with tar was a practice which gained far more currency than injection with chemicals, and it rose to popularity with the establishment of gasworks, of which tar was a cheap by-product. In 1858 the Melbourne Gas Works engineer A K Smith exhibited coal tar which he said was suitable for the preservation of timber. ²²⁴ In 1878 the stumps of a courthouse in Queensland were specified to be of ironbark or bloodwood 'slightly charred and twice

²¹⁸ Argus, 25 November 1857 & corrigendum, 26 November 1857. Again, see Lewis, 'Tradition and Innovation', for more detail.

Victorian patent no 508 granted to Richard Forrest, 26 October 1861.

Victorian patent no 593 granted to Frederick Ransome, 20 November 1862.

²²¹ C B Mayes, *Australian Builders' Price-Book* (Melbourne 1862), p 144.

Mayes, Australian Builders' Price-Book (1862), pp xiii, 151.

Victorian patent no 602 to Alan Cameron Lyster De Lacy, 30 December 1862.

Victoria Industrial Society, *Catalogue of the Eighth Annual Exhibition* (Melbourne 1858), p 43.

coated with hot coal tar + lime'. ²²⁵ In 1858 a patent was granted to James Thomson for what seems to have been some sort of a varnish, combining tar with other chemicals, ²²⁶ and another to W J Barton in 1860 for 'indurating and enamelling' wood and other substances with a solution of gas tar and resin. ²²⁷ Barton & Co are known to have used the process for stone preservation, though not necessarily for timber. However the 'oil of tar' which was produced by both the Melbourne and the Collingwood gasworks, was reported to be used on timber as a preservative. ²²⁸ This is presumably a reference to creosote.

The next phase of development involved the use of oils other than (or in addition to) creosote. During the 1880s a product called 'Carbolineum Avenarius' was marketed in Melbourne through an agent, F Messner, as a wood preservative as well as a waterproofing agent for brick and stone. Its composition was not stated, but it was not to be applied in the direct sun because it would cause 'an irritation of the skin of the face', which was inconvenient, though not dangerous. It was an oily fluid made up from tar oils, and had a strong tarry smell. It had been used extensively on German railways and public works, and was manufactured under patent by Avenarius Brothers of Gaulgesheim. ²³⁰

In 1887 it was announced that A M Fell & Son of Darling Harbour, Sydney, were supplying a wood preserving oil to prevent both dry rot and white ant, and that it was already in use by the government and several municipalities. However A R Taylor of New Farm, Brisbane, responded that the Fell oils had already been abandoned in Queensland after repeated trials, and that his own patent preparation was now used instead. In 1892 a resident of Merrigum, Victoria, recommended linseed oil into which pulverised coal had been mixed to bring it to the consistency of paint, which was guaranteed to prevent the rotting of posts in the ground. In 1919 ironbark and bloodwood were still being used in Queensland for stumps, but now 'twice (2) well coated with crude castor oil, well dusted over with arsenic after each coat where below ground and the remainder given two coats of well boiled coal tar, applied hot'. The use of arsenic indicates that this was now not merely a preservative but an ant-proofing measure, and such treatments will be further discussed below.

^{&#}x27;Specification of Work and material required in the erection of court house St Laurence', March 1878 [held by Historic Buildings Branch, Brisbane], no page.

Victorian patent no 91 granted to James Thomson, 17 March 1858.

Victorian patent no 393 granted to W J Barton, 9 October 1860.
Mayes, *Australian Builders' Price-Book* (1862), p 83.

Carbolineum Avenarius [leaflet] (Melbourne, no date), passim.

Australasian Ironmonger, 1 July 1887, p 176.

Australasian Builder & Contractor's News, 17 September 1887, p 297.

Australasian Builder & Contractor's News, 22 October 1887, p 391.

Farmer and Grazier, February 1892, p 38.

²³⁴ 'Specification: Erection and Completion of a new Rural School: Boonah', 17 February 1919 [held by Historic Buildings Branch, Brisbane], p 67.

Early in the twentieth century the 'Powellising' process was apparently regarded as effective even for hardwoods. It was marketed by the N.S.W. Powell Wood Process Ltd. of Sydney, and claimed to improve, strengthen and thoroughly season the timber. H D Walsh, Chief Engineer of the Harbor Trust, used powellised decking in some of his jetties and wharves. It was also carried out in Victoria, where it gave its name to Powelltown in the Little Yarra Valley, Gippsland. It has been reported as an English process which proved ineffective for Australian hardwoods, but this must be an overstatement, given that it was used for some time in this country. In 1928 the visiting expert A J Gibson spoke of Powellising as a process used for some years in Western Australia, though not apparently elsewhere, and referred also to experiments with creosoting at the University of Adelaide. 237

In Western Australia, apart from Powellising and creosoting, the Forests Department established a commercial operation to treat timber by the 'opentank method' in a solution of sodium fluoride and arsenic, patented as 'fluarizing'. Western Australian efforts were directed more at fence posts than at building scantling, but the range of preservatives in use is interesting - coal tar creosote was regarded as most effective; tar and petroleum oil were useful; but creosote and oil mixtures had some value, and were cheaper than pure creosote. There were also various proprietary oil preservatives, some of very little value. The water-soluble preservatives were sodium fluoride, zinc chloride, white arsenic, and various proprietary products. 238 When the Council for Scientific and Industrial Research came to produce its own circular on timber preservation, the means described were largely the same, but for the fact that copper sulphate, mercuric chloride and zinc metaarsenate had ben added to the list, though only the last was in any sense new.²³⁹

Cuprinol, advertised in 1936, was presumably (from the name) one of the treatments based upon copper compounds. It was claimed to be a fungicide and insecticide which penetrated deeply, and could be painted or varnished over. Water-soluble treatments such as 'Celcure' were later to become important in England, but much less so in Australia because they could be effective only with pine. In 1957, however, Australia's first industrial scale pressure impregnation plant was opened at South Grafton, New South Wales, capable of treating even dense Australian hardwoods, and first used

Building, 12 December 1911, p 34, and advertisement. p 23.

Paul Edwards, in *Royalauto*, November 1996, p 66.

A J Gibson, *A Forest Products Laboratory for Australia* [Council for Scientific and Industrial Research pamphlet no 9] (Melbourne 1928), p 16.

J E Cummins, *The Preservative Treatment of Fence Posts (with particular reference to Western Australia* [Council for Scientific and Industrial Research pamphlet no 24] (Melbourne 1932).

Journal of the Royal Victorian Institute of Architects, XXXIV, 4 (September 1936), p xxxvi.

The Preservation of Timber [trade circular no 27 of the Council for Scientific and Industrial Research, Division of Forest Products] (Melbourne 1935), pp 15-17.

Study Preservation of Timber [trade circular no 27 of the Council for Scientific and Industrial Research, Division of Forest Products] (Melbourne 1935), pp 15-17.

Evelyn Drury et al [eds], Architects', Builders' and Civil Engineers' Reference Book (London 1950), pp 147, 148, 154.

for electricity and telegraph poles.²⁴² In 1965 the Timber Preservers Association of Australia, apparently a recently formed body, published a seven page booklet, Timber Preservation in Australia. It described the two techniques in use, pressure impregnation and diffusion treatment. Pressure impregnation was used for the permanent protection of timber, and generally involved immersing the wood into a preservative solution in a cylinder at 200 psi [1380 kPa]. Diffusion treatment consisted simply of soaking. The preservatives were in two categories, water borne, which were generally of the copper-chrome-arsenate type, and oil-based, which were mostly creosote or pentachlorophenol dissolved in oil.²⁴³

h. antproofing

We have seen that the Fell oils and arsenic dust, were both used in treatments designed to prevent both decay and termite attack. But there were many other substances designed specifically to control white ants. Natal makes an interesting comparison with Australia, for not only was the use of stumps understood at an earlier date (as will appear below), but chemical treatments likewise. Early settlers had painted 'a low plinth' of Stockholm tar around the base of their buildings, though this proved ineffective. In 1864 a paint for outside walls was recommended, supposed to render them impervious to white ants and other insects. It was made of '11/2 bushels of grey lime, 11/2 bushels of Roman cement, 6 lb. of copperas, 6 lbs. of soft soap, 6 lbs. of sulphur, and as much yellow ochre as will bring the whole to any desirable colour. In 1866 creosote was advertised a protective material. In Rhodesia some pisé buildings had arsenate of soda or 'Atlas Compound' mixed into the lower layers to antproof them.

Peter Bell reports the use of treacle and arsenic against termites at Bowen in 1882, as prescribed in an unidentified 'official circular', and of Street's and Faulding's White Ant Poison, based on arsenic, as well as the procedure of steeping the stumps in creosote before they were used. As a prophylactic measure treacle and arsenic seemed, in at least one instance, only to render the timber more palatable, but Watson mentions a number of other chemicals which were used in Queensland. Carbolic acid and boiling water were applied to timber which was already under attack. Timbers were immersed in salt water, animal fats, oil or tar, or they were charred - all of which sound more like preservative than white ant measures. In the 1870s there appeared proprietary products such as the zinc-based compound marketed by Hiram

²⁴² Cross-Section, no 53 (1 March 1957), p 3.

Timber Preservers Association of Australia, *Timber Preservation in Australia* (Unley Park [South Australia] 1965), p [2].

Kearney, Architecture in Natal, p 68.

Kearney, Architecture in Natal, p 65, ref Davis' Natal Almanac of 1864.

Kearney, Architecture in Natal, p 65, ref H Brookes & Mann, Natal, a History and Description of the Colony (1876).

Clough Williams-Ellis, *Ćottage Building in Cob, Pisé, Chalk & Clay* (London 1919), pp 78-9.

Bell, *Timber and Iron*, p 163.

Wakefield,²⁴⁹ and in 1873 William Malpas of Athelstane, near Adelaide, obtained a patent for the use of copper sulphate combined with 'arsenious' acid and, optionally, sodium carbonate.²⁵⁰ This was applied to the lower timbers of an existing building at Caboolture in 1878. 'Taylor's Anti-termite' was in use in the 1880s, as were 'Anti-ant Wood Preservative', which was allegedly in use in India, China, Japan and elsewhere, and 'Antine', which was tried out at Inglewood and proved quite ineffective. By 1895 tar and arsenic had resumed their dominant position.

Some protection was gained simply by using cypress pine, a timber less palatable to ants, and clearing the site of all loose timber which might harbour them. In 1889 the Diocesan Architect, J H Buckeridge, examined the bell tower of the Anglican pro-cathedral in Brisbane, which had been constructed of English oak because this was thought to be termite-resistant. The hearts of the beams carrying the balls were completely eaten out. One of the legs, 450 mm square, was half eaten through to a height of nearly five metres. He replaced the damaged posts with Queensland hardwood on a concrete bed, and the treated the whole with an anti-termite preparation.

In 1906 'Solignum' wood preserver and white ant destroyer was being sold in Australia by Henry Books & Co.²⁵² In 1908 the Bain's White Ant Extermination Company of Sydney claimed to be contractors to the Commonwealth, New South Wales and West Australian governments, the Sydney Harbour Trust and the Federated Malay States, 253 and by the 1920s they called their product Bainal and claimed that it killed both the ants and the eggs.²⁵⁴ A liquid product called 'Jodelite' was claimed to be effective not only against the ant, but against fungus, dry rot and sea worm. ²⁵⁵ In about 1920 a chemical white ant preventative was regularly advertised in the post office directories in Queensland, 256 and soon 'Simplexol' was being sold by De Merin Ltd of Sydney. 257 In the 1920s the Borer & White Ant Exterminating Co of Victoria, was marketing 'Borantibane', with which they had treated nearly two thousand houses built by the State Savings Bank of Victoria. What it contained was unstated, but it was claimed to be lethal to borers, white ants, cockroaches, silverfish, spiders, flies, bugs, fleas, lice and other household pests. It was stainless, but left a lasting deposit of poison in treated timbers. 258 In 1949 'Solignum', which had been in existence for thirty years,

Watson, *The Queensland House*, pp 6.2-6.8.

Victorian patent no 1756, 1756A, to William Malpas, 214 April 1873. A second application by Malpas the following day, for the use of copper sulphate alone, was allowed to lapse.

Watson, *The Queensland House*, pp 6.2-6.8.

The Australasian Handbook Shippers, Importers and Professional Directory & Business Guide for 1906 (Gordon & Gotch, London 1906), p 4.

²⁵³ C E Mayes, *The Australian Builders and Contractors' Price-Book* (7th ed, Sydney 1908), p 226 & advertisements p xx.

Building, 12 October 1923, p 43.

Mayes, Australian Builders Price-Book (1908), p 22

Information from Peter Marquis-Kyle, 1991.

²⁵⁷ Building, 12 October 1923, p 43.

The Borer & White Ant Exterminating Co of Victoria, *The Great Menace to Our Homes* [brochure] (Melbourne, no date [late 1920s]), passim.

was being advertised in Australia as a 'wood preserving stain' and white ant and borer destroyer. However it was an English product, and references were cited from Khartoum, so there is no clear evidence of its use in Australia. Indeed it is a moot point whether the 'remarkable penetration' claimed in the advertising, would have had any impact on Australian hardwoods.

In 1955 T Maxwell, a Sydney pest control contractor, demonstrated a system of 'permanently installed' poison sprays. Dunlop Flexatube plastic tubing was attached to each bearer and pierced near every stump, and poison was fed into the system every four months by the householder, using a stirrup pump. In the following year it was reported that the new Parliament House in Darwin was suffering white ant attack even before it was completed, the ants having already eaten through a concrete slab and attacked the joinery. Potentially more serious news was that the European borer, new to Australia, had been found attacking the softwoods in some Brisbane buildings, and was being combatted by the Queensland Department of Forests.

F Wentworth & W L Richardson [eds], Ramsay's Architectural and Engineering Catalogue (Melbourne 19549), §32,3.

²⁶⁰ Cross-Section, no 37 (1 November 1955), p 2.

²⁶¹ Cross-Section, no 44 (1 June 1956), p 2.

²⁶² Cross-Section, no 48 (1 October 1956), p 2.